

EPDM RUBBER

דר DANILOV
דרילוב החברה למסחר בע"מ
בן ציון גליס 15, פתח תקווה.
טל: 052-770064 (2004)
sales@danilov-trading.co.il

TECHNICAL DATA SHEET

No.			
	Item		Index
1	Tensile Strengtl (N/cm)	h Room temperature ≥	7.5
		60℃ ≥	2.3
2	Elongation at break (%)	Room temperature ≥	450
		-20℃	200
3	Tear strength (kN/m)≥		25
4	Water tightness, 30min no leak		0.3Мра
5	Low temperature bending(°C)		-40
	Elongation and	Extension ≤	2
6	shrinkage after heating(mm)	Shrinkage ≤	4
7	Hot air aging	Conservation rate of tensile	80
	(80°C×168h)	strength at break % ≥	
		Conservation rate of elongation at break % ≥	70
8	Alkali resistance [Saturated solution Ca(OH)2 Normal temp.×168h]	Conservation rate of tensile strength at break % ≥	80
		Conservation rate of elongation at break % ≥	80
9	Ozone aging(40 °C×168h)	Elongation 40%, 500pphm	No crack
10	Artificial weathering aging	Conservation rate of tensile strength at break % ≥	80
		Conservation rate of elongation at break % ≥	70
11	Peel strength of bonding	(N/mm)(standard test condition) ≥	1.5
		Conservation rate after immersion (Normal temp.×168h) % ≥	7.0

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in maccordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

